

Ni-CD Battery Technology Specification

Reference BAT1008

Part name Ni-CD Battery

Model No Ni-Cd SC1800mAh 1.2V

1. SCOPE

This specification governs the performance of the following Ni-Cd battery Cylindrical Cell and its stack-up batteries.

Model: Ni-Cd SC1800mAh 1.2V

The data involving nominal voltage and the approximate weight of stake-up batteries shall be equal to the value of the unit cell multiplied by the number of unit cells in the battery.

Nominal voltage of unit cell = 1.2V

2. RATINGS

Description	Unit	Specification	Conditions
Nominal Voltage	V	1.2	
Nominal Capacity	mAh	1800	Standard Charge/discharge
Minimum Capacity	mAh	1710	Standard Charge/discharge
Standard Charge	mA	180(0.1C)	Ta=0~45°C
	hour	14-16	
Fast Charge	mA	900(0.5C)	-ΔV=5~10mV/pcs Timercutoff=110%input capacity Temp.cutoff=55°C ⁻² Ta=10~45°C
	hour	2.4approx	
Trickle Charge	mA	90(0.05C) ~ 180(0.1C)	Ta=0~45 °C
Discharge Cut-off Voltage	V	1.0	Ta=-20~55°C
Maximum Discharge Current	mA	3600 (2C)	Ta=10~45°C
Storage Temperature	°C	-20~35°C	Discharge state

3. PERFORMANCE

Unless otherwise stated, tests should be done within one month of delivery under the following conditions:

Ambient Temperature: Ta=20±5°C

Relative Humidity: 65±20%

Standard Charge/ Discharge Condition:

Charge: 180mA(0.1C)×16hrs

Discharge: 360mA(0.2C)to1.0V/ cell

Table 1

Test	Unit	Specification	Conditions	Remarks
Capacity	mAh	≥ 1710	Standard Charge/Discharge	Up to 3 cycles are allowed
Open Circuit Voltage (OCV)	V	≥ 1.25	Within 1hr after standard charge	
Internal Impedance (Ri)	m Ω	≤ 20	Upon fully charge(1kHz) (1kHz)	
High Rate Discharge (0.5C)	min	≥ 108	Standard Charge, 1hr rest before discharge	
High Rate Discharge (1C)	min	≥ 54	Standard Charge, 1hr rest before discharge	
Overcharge	N/A	No leakage nor explosion	180mA(0.1C) charge 48 hours	
Charge Retention	mAh	$\geq 1080(60\%)$	Standard Charge, Storage: 7 days at 45°C, 0.2C Standard Discharge	
IEC Cycles Test	Cycle	≥ 300	IEC61951-1 (2003)	- 3 -

Table 2

Test	Unit	Specification	Conditions
Leakage	N/A	No leakage nor deformation.	Full charged at (0.1C) stand for 14 days
Short Circuit	N/A	Leakage & deformation may occur, but no explosion is allowed.	After standard charge, short circuit for 1 hour (leading wire=0.75mm ² ×20mm)
Vibration Resistance	N/A	Change of voltage $\Delta V < 0.02V$, Change of internal Impedance $\Delta Ri < 5 m\Omega$.	Charge the battery 0.1C 16hrs, then leave for 24hrs. check battery before / after vibration. Amplitude: 1.5mm Vibration: 3000CPM Any direction for 60mins.

4. CONFIGURATION, DIMENSIONS AND MARKINGS

Please refer to the attached drawing.

5. EXTERNAL APPEARANCE

The cell/ battery shall be free from cracks, scars, breakage, rust, Discoloration, leakage nor deformation.

6. CAUTION


- ◆.Reverse charging is not acceptable
- ◆.Do not burthen current when charging.
- ◆.Do not charge/discharge with more than the specified current.
- ◆.Do not short circuit the cell/ battery. Permanent damage to the cell/ battery may result.
- ◆. Do not incinerate or mutilate the cell/ battery.
- ◆.Do not subject batteries to adverse conditions like: extreme temperature, deep cycling and excessive Overcharge/overdischarge.The life expectancy may be reduced.
- ◆.Store the cell/ battery in a cool dry place. Always discharge the cell/battery before bulk storage or shipment.
- ◆. Cycle(charge and discharge) the battery every 6-9months to maintain cell/battery performance when being stored for an extended period of time.
- ◆.Keep away from children. If swallowed, contact a physician at once.
- ◆. Avoid airtight battery compartments. Ventilation should be provided in the plastic case of batteries, otherwise oxygen and hydrogen gas generated inside -4- can cause explosion when exposed to fire sources such as motors or switches.

Remark:

IEC61951-1(2003) Cycle Life Test:

Cycle	Charge	Rest	Discharge
1	0.1C×16hrs	\	0.25C×2hrs20mins
2-48	0.25C×3hrs10mins	\	0.25C×2hrs20mins
49	0.25C×3hrs10mins	\	0.25Cto1.0/cell
50	0.1C×16hrs)	1-4hr(s)	0.2Cto1.0/cell
Cycle 1 to 50 shall be repeated until the discharge duration on any 50 th cycle becomes less than 3hrs			

7. Dimensions of the battery:



- 5 -

.....END.....